

PSX 1001

Single pack acrylic polysiloxane (1001 Series)

Product Data/ Application Instructions

- Single component
- Non-isocyanate
- Outstanding weather resistance with excellent colour and gloss retention
- Resists soil pick up - easily cleanable
- Cures through a wide temperature range
- Easily recoated with itself with an unlimited recoat window
- Brush/roll/spray application

As a finish coat where an attractive appearance and excellent weathering resistance is required for chemical plants, pulp and paper mills, petroleum refineries, offshore platforms, marine equipment, ship topsides and other equipment.

PSX 1001 provides a polyurethane-like finish, in one component without the isocyanate, as well as better weathering than standard aliphatic polyurethane.

Used with Amercoat 185 HS or Amercoat 5105 primer to give a high performance maintenance system with the ease of single pack application.

Systems Using PSX 1001

First coat	Finish coat
Amerlock 2C	PSX 1001
Amercoat 185HS or Amercoat 5105	PSX 1001
Amercoat 182ZP HB or Amercoat 71 primer or Amercoat 71TC	PSX 1001
Amercoat 370	PSX 1001
Amercoat 229 Series, 450 Series, PSX 700, Amershield	PSX 1001

PSX 1001 should not be used with Amercoat 385.

Physical Data

Finish	High gloss	
Colour.....	RAL and BS colours*	
Components	1	
Mixing ratio (volume).....	NA	
Curing mechanism	solvent evaporation and reaction between components	
Volume solids	55% (ISO 3233)**	
VOC***		
EC SED 1999/13/EC	289 g/kg (390 g/l)	
UK PG6/23(92) Appendix 3	384 g/l (3.2 lbs/gal)	
Dry film thickness	50-75 microns 2- 3 mils	
Number of coats	1****	
Theoretical coverage.....	m ² /L	ft ² /gal
at 50 microns / 2 mils dft.....	11	456
at 75 microns / 3 mils dft.....	7.3	304
Temperature resistance	°C	°F
Continuous.....	93	200
Intermittent.....	120	250
Flashpoints	°C	°F
PSX 1001.....	19	66
Amercoat 911	27	81
Amercoat 12	24	75
Thinners	Amercoat 911	
Cleaner	Amercoat 12	

* On tanks and other large structures previously coated with contrasting primer or intermediate coats, uniform appearance may require two coats of PSX 1001. Use only a light colour primer or intermediate coat when only one finish coat of PSX 1001 in a light colour is specified.

** Volume solids is measured in accordance with ISO 3233. Slight variations ±3% may occur due to colour and testing variances.

*** VOC figures are quoted according to both the EC directive 1999/13/EC which are theoretically calculated figures and the UK PG6/23(92) Appendix 3 which are practically determined figures.

**** Brush or roller application may require additional coats.

PSX 1001

Chemical Resistance Guide

(when applied over suitable primer or intermediate coat)

Environment	Splash and Spillage	Fumes and Weathering
Acidic	No	Yes
Alkaline	Yes	Yes
Petroleum products	Yes	Yes
Solvents	No	No
Salt solutions		
Acidic	Yes	Yes
Neutral	Yes	Yes
Alkaline	Yes	Yes
Water	Yes	Yes

This chart is only a guide to show typical resistances of PSX 1001 your PPG representative will help you evaluate your particular corrosion protection needs and make the correct recommendation for your specific requirements. PSX 1001 is not recommended for immersion service.

Surface Preparation

STEEL - Prepare surface in accordance with application instructions for the specific primer being used. Be sure primer is clean and dry when PSX 1001 is applied.

Application Equipment

The following equipment is listed as a guide and suitable equipment from other manufacturers may be used. Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

AIRLESS SPRAY - Standard airless spray equipment, having a fluid tip with a 0.33 to 0.43 mm (0.013 to 0.017 inch) orifice.

CONVENTIONAL SPRAY with 78 or 765 air cap and "E" fluid tip or a 66 x 63 PB nozzle setup.

Separate air and fluid pressure regulators, mechanical pot agitator and a moisture and oil trap in the main air supply line are recommended.

MIXER - Use power mixer powered by an air motor or an explosion proof electric motor.

Substrates Prepared and primed steel coated with Am 71, Am 71TC,

182ZP HB, 185HS, 370, 5105, PSX 700 or Amerlock 2C

Surface preparation..... Refer to Typical Systems for specific primer or intermediate coatings recommended.

Application method..... Airless or conventional spray, brush or roller.

Environmental conditions

Air temperature 4 - 43 °C 40 - 110 °F

Surface temperature..... 4 - 43 °C 40 - 110 °F

Surface temperature must be at least 3°C / 5°F above the dew point to prevent moisture condensation on the surface.

Drying Times at 60% Relative Humidity average

Drying times (°C/°F)	49/120	32/90	21/70	10/50
Dry to touch	½ hr	1 hrs	2 hrs	3 hrs
Dry through.....	3 hrs	8 hrs	12 hrs	24 hrs

Recoat times (°C/°F)	49/120	32/90	21/70	10/50
Minimum times (hrs)				
Amercoat 185HS	1	2	2 ½	4
Amercoat 370	¼	½	1	3
Amerlock 2C	3	7	14	28

Application Data



PSX 1001

Application Procedure

PSX 1001 is packaged 20 l in 20 l can
The product is reactive with moisture. Keep containers dry and tightly sealed when not in use for mixing or application.

1. Flush equipment with recommended cleaner before use.
2. Stir to a uniform consistency with a power mixer.
3. For spray application, thin only as needed for workability with no more than 10 vol % of recommended thinner. For application at temperatures below 10°C, more thinner may be required to ensure proper atomising. NOTE: For brushing and rolling, normally no thinning is required.
4. Apply a wet coat in even, parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
5. Double coat all welds, rough spots, sharp edges and corners, rivets, bolts, etc.
6. Application at 90 µm wet film thickness will normally provide 50 µm dry film.
7. Check thickness of dry coating with a non-destructive dry film thickness gauge, such as Mikrotest or Elcometer. If less than specified thickness, apply additional material as needed.
8. Small damaged or bare areas and random pinholes or holidays can be touched up by brush. Repair larger areas by spray.
9. In confined areas ventilate with clean air during application and drying until all solvents are removed. Temperature and humidity of ventilating air must be such that moisture condensation will not form on surface.
10. Clean all equipment with recommended cleaner immediately after use or at least at the end of each working day or shift. When left in spray equipment, PSX 1001 may cause clogging.

Repair

For repair, or application of additional thickness, PSX 1001 may be overcoated with itself unlimited. Ensure surface is clean prior to application.

Shipping Data

Packaging	
Large.....	20 L in 20 L can
Small.....	5 L in 5 L can

Shipping weight	kg	lb
Large.....	approx. 29	64
Small.....	approx. 7	16

Shelf life	
Resin and cure	1 year from shipment date when stored indoors in unopened, original containers at 5 to 40°C (41 to 104°F)



PSX 1001

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

PPG warrants its products to be free from defects in material and workmanship. PPG's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at PPG's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall PPG be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by PPG, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

PPG's liability on any claim of any kind, including claims based upon PPG's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall PPG be liable for consequential or incidental damages.

Due to PPG's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the PPG Protective & Marine Coatings website at www.ppgpmc.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

