

STEELGUARD™ 651

DESCRIPTION

One-component, thin-film, waterborne intumescent coating for fire protection of structural steelwork

PRINCIPAL CHARACTERISTICS

- Provides up to 120 minutes protection from cellulosic fires
- On-site application
- Up to 700 µm (28.0 mils) DFT in a single coat
- Suitable for C1, C2 and C3 internal environments (ISO 12944) ; for dry internal (C1) environments no topcoat is required
- Tested and assessed to EN13381-8, BS476-20/21 and GB14907
- CE Marked product, ETA 15/0524
- Assessed to ETAG 018-2 for durability classifications Z1, Z2 and Y

COLOR AND GLOSS LEVEL

- White
- Matt

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.41 kg/l (11.77 lb/US gal)
Volume solids	70 ± 3%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 0.2 g/kg EUR Directive: 2004/42/IIA(i)(140) 3 g/l
Recommended dry film thickness	200 - 700 µm (8.0 - 28.0 mils) per coat
Theoretical spreading rate	1.00 m ² /l for 700 µm (40 ft ² /US gal for 28.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 16 hours Maximum: Unlimited
Shelf life	At least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time
- The required dry film thickness must be in accordance with the approval certification
- Materials should be stored in dry conditions, out of direct sunlight and at temperature between 10°C (50°F) and 30°C (86°F). Shelf life may be reduced by storage at low temperatures, material must not be allowed to freeze

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Approved primer must be sound, dry and free from any contamination



STEELGUARD™ 651

Substrate temperature and application conditions

- Substrate temperature during application and curing should be between 10°C (50°F) and 40°C (104°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Ambient temperature during application and curing should be between 10°C (50°F) and 40°C (104°F)
- Relative humidity during application and curing should not exceed 80%

Note: Over application will extend drying/curing times. Care should be taken in areas such as flange/web interfaces as excessive film build can result in small hairline cracks. This cracking will not affect the fire performance of the material.

INSTRUCTIONS FOR USE

- Stir thoroughly until homogeneous and free of lumps
 - Adding too much water results in reduced sag resistance and slower cure
 - Must be protected from freezing at all times during storage and/or transport
-

Airless spray

Recommended thinner

Tap water (normally no thinner required)

Volume of thinner

0 - 5%

Nozzle angle

20° - 50°, depending on shape of steel parts

Nozzle orifice

Approx. 0.43 - 0.53 mm (0.017 - 0.021 in)

Nozzle pressure

20.0 MPa (approx. 200 bar; 2901 p.s.i.)

Notes:

- All filters, including surge bottle and gun filters to be removed
 - External fluid uptake pipe filter is recommended
-

Brush/roller

- For small areas only (touch up and repair)

Recommended thinner

No thinner should be added

Cleaning solvent

Tap water



STEELGUARD™ 651

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
200 µm (8.0 mils)	3.50 m ² /l (140 ft ² /US gal)
400 µm (16.0 mils)	1.75 m ² /l (70 ft ² /US gal)
500 µm (20.0 mils)	1.40 m ² /l (56 ft ² /US gal)
700 µm (28.0 mils)	1.00 m ² /l (40 ft ² /US gal)

Note: Maximum DFT when brushing: 300 µm (12.0 mils)

Overcoating interval for DFT up to 700 µm (28.0 mils)					
Overcoating with...	Interval	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	24 hours	20 hours	16 hours	12 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited
approved topcoats	Minimum	24 hours	20 hours	18 hours	14 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Note: Above data is subject to sufficient airflow and ventilation

Curing time for DFT up to 700 µm (28.0 mils)	
Substrate temperature	Dry to touch
10°C (50°F)	4 hours
15°C (59°F)	3 hours
20°C (68°F)	2 hours
30°C (86°F)	1 hour

Note: Drying times may vary considerably depending on ambient conditions, A/V m³ (Hp/A) of section and applied film thickness

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a waterborne paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes

STEELGUARD™ 651

REFERENCES

• STEELGUARD™ APPLICATION GUIDELINES	INFORMATION SHEET	1222
• STEELGUARD™ QUALIFIED PRIMERS	INFORMATION SHEET	1224
• STEELGUARD™ QUALIFIED TOPCOATS	INFORMATION SHEET	1226
• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

